



INDUSTRIAL TECHNOLOGY INSTITUTE (ITI)

P. O. Box, 787, 363, Bauddhaloka Mawatha, Colombo 7, Sri Lanka.

Telephone: +94 11 2379800 Fax: +94 11 2379850

120/4A, Vidya Mawatha, Colombo 7, Sri Lanka.

Telephone: +94 11 2379800 Fax: +94 11 2379950

503/A, Halbarawa Gardens, Thaladena, Malambe, Sri Lanka.

Telephone: +94 11 2797300 Fax: +94 11 2379848

TEST REPORT

Report No. SS 2113334

Report to :

Horana Minerals (Pvt) Ltd,
No: 05, Gonamadiththa,
Watte, Thalawa,
Haltota.

Issued By :

Materials Laboratory,
Industrial Technology Institute,
363, Bauddhaloka Mawatha,
Colombo 07.

2021-11-17

Page 01 of 03 Pages

THE REPORT IS ISSUED SUBJECT TO CONDITIONS MENTIONED OVERLEAF

"PLEASE ADDRESS ALL COVERS TO THE DIRECTOR GENERAL"

The Report is issued under the following conditions:

CONFIDENTIALITY: Strict Confidentiality is maintained in all interactions with clients. The client must not use the Industrial Technology Institute (ITI) name and / or data in any manner, which might cause harm to the institute's reputation and / or business. Under no circumstances is the name of the institute, to be published either alone or in association with that of any other party without prior written approval from the Director General of the Institute.

TEST/CALIBRATION METHODS: In the absence of a specific request from the customer, ITI will adopt any appropriate national/international standard method for conducting the test/calibration. In the absence/non accessibility of standard methods, ITI may adopt any other relevant published test/calibration method or follow a method developed at ITI.

TEST/CALIBRATION REPORT: 1. The report is issued for the information of the customer and shall not be reproduced in total or in part without the prior written authority of the Director General, ITI. Any person or any party who alters or adds or deletes or interpolates any provisions or words or letters or figures shall be liable to legal action. 2. The report is not a Certificate of Quality. It only applies to the item of the specific product/equipment tested/calibrated or to the consignment/lot/batch from which a representative sample has been drawn by ITI. The results shall not be used to indicate or imply that they are applicable to other similar items. In addition such results must not be used to indicate or imply that ITI approves, recommends or endorses the manufacturer, supplier or user of such product/equipment or that ITI in any way guarantees the later performance of the product/equipment. 3. The report furnished by ITI shall not be used in any advertising or sales promotion without the prior written authority of the Director General ITI. 4. The report is limited specifically to the item/s submitted unless otherwise mentioned. 5. Conformities to a standard specifications may be mentioned as required by standard specification on request by the customer. 6. The ITI will not offer any opinion/advise or recommendation with respect to the suitability or otherwise of the item for any application or use. Interpretation of results and professional opinion and recommendations if required should be requested by customer and will be provided for an additional fee paid for by customer. 7. Under no circumstances does the ITI accept any liability or loss or damage caused by misuse of the ITI report. Liability is limited to the fee charged in case of proven negligence by the ITI.

COPIES OF REPORT: Only one copy of the report will be made available to the customer. Extra copies if necessary could be requested by customer at the time of submission of job and will be provided on the payment of an extra charge. Additional copies of the report endorsed by the Authorized signatory could be made available at the request of the customer within a period of 01 year from the date of issue of report, on a written request by the customer and on payment of an extra charge. No third party can obtain such a report without written authorization from the customer to ITI.

QUERIES ON REPORT: Customer queries on reports will be entertained only up to a period of 01 year from the date of issue of the report.


RETENTION OF TEST ITEMS: Perishable items will be destroyed immediately after testing, other items after 01 month from the date of issue of the report.

RETURN OF TEST ITEMS: Test items will be returned to the customer at the sole discretion of the ITI only on a written request by the customer.

LOSS OR DAMAGE: While the ITI exercises every care in respect of work entrusted to the Institute by customers, the Institute is not liable for any loss/damage howsoever caused to person/property, including property entrusted by customer to the Institute whether such loss, damage or delay may have been caused by reasons beyond the control of the Institute or otherwise.

LITIGATION: All costs associated with litigation or dispute for oral or written testimony or preparation of same or for any other purpose related to work provided by the ITI shall be paid by the customer. Such costs include, but are not limited to hourly charges, travel and accommodation, mileage, counsel, legal fees and all other expenses associated with the said litigation and dispute.

CHANGE OF CONDITIONS: ITI may at its sole discretion add to or amend the conditions of this report at the time of issue of the report and such additions or amendments shall be binding on the customer.




TEST REPORT


Report No. SS 2113334

Customer : Horana Minerals (Pvt) Ltd, No: 05, Gonamadiththa, Watte, Thalawa, Haltota.	Test Item : Wall Putty Service Requested : Customer's letter date 2021-10-07.
Description : One (01) test item. Test item was packed in polythene bag. (About 25kg.)	Identification of Test Item : Test item was labelled as: Product Name - Silky Interior Total Finish HEGA Wall putty - White Marketed by - Horana Minerals (Pvt) Ltd. No: 05, Gonamadiththa Watte, Thalawa, Haltota. Sri Lanka. Date of Receipt of Test Item : 2021-10-07
Test Dates : From 2021-11-08 to 2021-11-10	

TEST RESULTS :

Test/ Unit	Test Method	Result
1. Moisture / % by mass	Gravimetry	0.35
2. pH at 26 °C (10% solution)	Using pH meter	11.0


.....
Authorized Signatory
C.N. Vitharana
Research Engineer
Materials Laboratory
2021-11-17
-/lp.


.....
Anusha Dasanayaka
Assistant Research Technologist